

MATERIAL AND EQUIPMENT STANDARD

FOR

SILICONE ALKYD PAINT (WHITE OR COLORED EXCEPT BLACK)

AS

TOP COAT (FINISH)

ORIGINAL EDITION

MAY 1993

This standard specification is reviewed and updated by the relevant technical committee on Sep. 1998(1) and Aug. 2014(2). The approved modifications are included in the present issue of IPS.

FOREWORD

The Iranian Petroleum Standards (IPS) reflect the views of the Iranian Ministry of Petroleum and are intended for use in the oil and gas production facilities, oil refineries, chemical and petrochemical plants, gas handling and processing installations and other such facilities.

IPS is based on internationally acceptable standards and includes selections from the items stipulated in the referenced standards. They are also supplemented by additional requirements and/or modifications based on the experience acquired by the Iranian Petroleum Industry and the local market availability. The options which are not specified in the text of the standards are itemized in data sheet/s, so that, the user can select his appropriate preferences therein

The IPS standards are therefore expected to be sufficiently flexible so that the users can adapt these standards to their requirements. However, they may not cover every requirement of each project. For such cases, an addendum to IPS Standard shall be prepared by the user which elaborates the particular requirements of the user. This addendum together with the relevant IPS shall form the job specification for the specific project or work.

The IPS is reviewed and up-dated approximately every five years. Each standards are subject to amendment or withdrawal, if required, thus the latest edition of IPS shall be applicable

The users of IPS are therefore requested to send their views and comments, including any addendum prepared for particular cases to the following address. These comments and recommendations will be reviewed by the relevant technical committee and in case of approval will be incorporated in the next revision of the standard.

Standards and Research department

No.17, Street14, North kheradmand

Karimkhan Avenue, Tehran, Iran.

Postal Code- 1585886851

Tel: 021-88810459-60 & 021-66153055

Fax: 021-88810462

Email: Standards@nioc.ir

GENERAL DEFINITIONS:

Throughout this Standard the following definitions shall apply.

COMPANY:

Refers to one of the related and/or affiliated companies of the Iranian Ministry of Petroleum such as National Iranian Oil Company, National Iranian Gas Company, National Petrochemical Company and National Iranian Oil Refinery And Distribution Company.

PURCHASER:

Means the "Company" where this standard is a part of direct purchaser order by the "Company", and the "Contractor" where this Standard is a part of contract documents.

VENDOR AND SUPPLIER:

Refers to firm or person who will supply and/or fabricate the equipment or material.

CONTRACTOR:

Refers to the persons, firm or company whose tender has been accepted by the company.

EXECUTOR:

Executor is the party which carries out all or part of construction and/or commissioning for the project.

INSPECTOR:

The Inspector referred to in this Standard is a person/persons or a body appointed in writing by the company for the inspection of fabrication and installation work.

SHALL:

Is used where a provision is mandatory.

SHOULD:

Is used where a provision is advisory only.

WILL:

Is normally used in connection with the action by the "Company" rather than by a contractor, supplier or vendor.

MAY:

Is used where a provision is completely discretionary.

CONTENTS :

PAGE No.

1. SCOPE	1
2. REFERENCES	1
3. UNITS	2
4. COMPOSITION	3
5. ANALYSIS	4
6. PROPERTIES	5
7. STORAGE LIFE AND PACKAGING	7
8. INSPECTION	7
9. LABELING	7

1. SCOPE

This Standard specification which is mainly generated from SSPC paint No. 21 covers the minimum requirements for the composition, analysis, properties, storage life and packaging, inspection and labeling of silicone alkyd paint as top coat (finish).

Note:

This standard specification is reviewed and updated by the relevant technical committee on Sep. 1998. The approved modifications by T.C. were sent to IPS users as amendment No. 1 by circular No. 66 on Sep. 1998. These modifications are included in the present issue of IPS.

2. REFERENCES

Throughout this Standard the following dated and undated standards/codes are referred to. These referenced documents shall, to the extent specified herein, form a part of this standard. For dated references, the edition cited applies. The applicability of changes in dated references that occur after the cited date shall be mutually agreed upon by the Company and the Vendor. For undated references, the latest edition of the referenced documents (including any supplements and amendments) applies.

SSPC (STEEL STRUCTURES PAINTING COUNCIL) VOL. 2

SSPC No. 21	"White or Colored Silicone Alkyd Paint- Type I: High Gloss, Type II: Medium Gloss"
SSPC-PA Guide 3,	"A Guide to Safety in Paint Application"

ASTM (AMERICAN SOCIETY FOR TESTING AND MATERIALS)**(Specification for Ingredients)**

D235	"Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvent)"
D476	"Dry Pigmentary Titanium Dioxide Products"
D600	"Liquid Paint Driers"

(Specification for Packaging)

D3951	"Standard Practice for Commercial Packaging"
-------	--

(Test Methods for Properties)

D93	"Flash Point by Pensky-Martens Closed Tester"
D95	"Water in Petroleum Products and Bituminous Materials by Distillation"
D185	"Coarse Particles in Pigments"
D562	"Consistency of Paints Measuring Krebs Unit (KU) Viscosity Using a Stormer-Type Viscometer"
D1210	"Fineness of Dispersion of Pigment-Vehicle Systems by Hegman-Type Gage"
D1296	"Odors of Volatile Solvents and Diluents"

D1640	"Drying, Curing, or Film Formation of Organic Coatings at Room Temperature"
D1729	"Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials"
D1849	"Package Stability of Paint"
D2244	"Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates"
D2369	"Volatile Content of Coatings"
D2371	"Pigment Content of Solvent-Reducible Paints"
D2698	"Determination of the Pigment Content of Solvent-Reducible Paints by High-Speed Centrifuging"
D2805	"Hiding Power of Paints"

UFS (US FEDERAL STANDARDS)

(Federal Test Method Standard No. 141)

Section 9	"Routine and Referee Testing Conditions"
Method 3011	"Condition in Container"
Method 4061	"Drying Time"
Method 4081	"Water Content (Reflux Method)"
Method 4203	"Reducibility and Dilution Stability"
Method 4321	"Brushing Properties"
Method 4331	"Spraying Properties"

(US Federal Standard No. 595 Colors Used in Government Procurement)

ANSI (AMERICAN NATIONAL STANDARDS INSTITUTE)

ANSI Z400.1/Z129.1	"Hazard Evaluation and Safety Data Sheet and Precautionary Labeling Preparation"
--------------------	--

BSI (BRITISH STANDARD INSTITUTION)

BS 381C	"Colors for Identification, Coding and Special Purposes"
---------	--

IPS (IRANIAN PETROLEUM STANDARDS)

IPS-E-GN-100	"Units"
IPS-E-TP-100	"Paints"

3. UNITS

This Standard is based on International System of Units (SI), as per [IPS-E-GN-100](#) except where otherwise specified.

4. COMPOSITION

4.1 Ingredients and Proportions

Ingredients and proportions shall be as specified in Table 1 and sections 4.2 through 4.6.

4.2 Percentage

This paint shall contain a minimum of 60-67% by volume of nonvolatile film forming solids (pigments and binder).

4.3 Pigments

The main pigment for white shall consist of titanium dioxide conforming to ASTM-D-476, Type IV, or any combination of colored pigments to obtain the color specified, provided the paint complies with the requirements of this specification.

4.4 Vehicle

The vehicle shall consist of silicon-modified medium oil soya alkyd copolymer of the air-drying type, together with suitable thinners, driers, anti-skinning agents, wetting agents, dispersing agents, and stabilizers combined, producing a material conforming to all requirements specified herein. The silicone intermediate used in the preparation of the copolymerized resin shall be hydroxy functional. The vehicle shall conform to the composition (analysis) requirements of Table 2.

4.5 Solvent

The solvent shall be mineral spirits conforming to ASTM-D.

4.6 Driers

The driers shall conform to ASTM-D 600.

TABLE 1 - COMPOSITION

COMPOSITION		
INGREDIENTS	Wt. %	INGREDIENT STANDARDS
TOTAL SOLIDS	50-70	ASTM D2369
VEHICLE SOLIDS	30-40	---
SOLVENTS	30-40	---

Note:

Vehicle Solids

Place a portion (approximately 10 grams) of the vehicle (Separated as in ASTM Standard D2698) in a dropping bottle and weigh to the nearest 0.1 mg. Weigh one of the 60 mm aluminum dishes with fourth decimal-place accuracy. Transfer a small sample that does not exceed 0.3 grams to the dish, and determine its exact weight by loss of weight of the bottle. Dissolve the sample in 2 ml of reagent grade toluene and dry in a gravity convection oven at 105 ±2°C for three hours. After cooling for 30 minutes, weigh the dish to the nearest 0.1 mg. From the weight of residue in the dish and the weight of the sample taken, calculate the percent vehicle solids.

TABLE 2 - VEHICLE CHARACTERISTICS

CHARACTERISTICS	REQUIREMENTS		ASTM METHOD	US FEDERAL STD. No. 141
	Min.	Max.		
COPOLYMER RESIN SOLIDS, PERCENT BY WEIGHT OF EXTRACTED VEHICLE SOLIDS ¹	50.0	---	---	---
SILICA (SiO ₂), PERCENT BY WEIGHT OF COPOLYMER RESIN SOLIDS ²	14.0	---	---	---
PHTHALIC ANHYDRIDE, PERCENT BY WEIGHT OF COPOLYMER RESIN SOLIDS	14.0	17.0	---	---
SOYA OIL ACID CONTENT (BASED ON SOLIDS)	41.0	55.0	---	---
SOYA OIL	POSITIVE		---	---

1) Copolymer resin content of nonvolatile vehicle isopropanol extraction: Weigh five grams (to the nearest 0.1 mg) of vehicle (separated as in ASTM D2698) into a tared centrifuge bottle or tube fitted with a cap. Add 50 ml of isopropanol (technical grade), cap the bottle or tube, and shake vigorously for two minutes. Centrifuge for 15 minutes at a minimum of 2,000 rpm. Decant the isopropanol extract and repeat the extraction and condition the bottle or tube in 135°C oven for three hours. Remove the bottle or tube, cool for 30 minutes at room temperature, and weigh. Calculate the copolymer resin solids using the following formula.

$$\text{Percent copolymer resin solids} = \frac{R \times 100}{S \times D}$$

Where:

R = Weight of residue (in the bottle or tube)

S = Weight of sample (vehicle)

D = Percent of vehicle solids (see Note, Table 1)

2) Silica Content of Vehicle: From a stoppered bottle or weighing pipet, weigh accurately by difference, about 3 grams of the vehicle into a properly ignited and weighed 75 mm porcelain evaporating dish. Dry at 105°C in an oven for 3 hours. Place the dried sample in a cold muffle furnace and gradually increase the temperature over a period of 3 hours to 800°C. Then maintain this temperature for an additional hour. After cooling in a dessicator, weigh the dish and contents and calculate the percent of silica as follows:

$$\text{Percent Silica} = \frac{A \times 100}{S \times D}$$

Where:

A = Weight of ash

S = Weight of sample (vehicle)

D = Percent of vehicle solids (see note, Table 1)

5. ANALYSIS

The high gloss white paint shall conform to the composition (analysis) requirement of Table 3.

TABLE 3 - ANALYSIS FOR WHITE

CHARACTERISTICS	REQUIREMENTS		ASTM METHOD
	Min. Wt. %	Max. Wt. %	
TOTAL SOLIDS	64	---	D2369
PIGMENT SOLIDS	31	35	D2371
VEHICLE SOLIDS	37	---	SEE NOTE, TABLE 1

6. PROPERTIES

6.1 The paint shall meet the requirements of Table 5 and sections 6.2 through 6.9.

6.2 Odor

The odor shall be normal for the materials permitted (ASTM Standard D1296) The odor of the wet enamel and of the film at any interval of drying shall not be obnoxious or objectional.

6.3 Color

Draw down a coat of paint on a white opaque glass panel using a doctor blade with a 150 microns gap clearance designed to deposit a wet film thickness of approximately 75 microns. After 48 hours drying at 21-24°C and 50% relative humidity, compare the dried film with the Standard chip (US Federal Standard No. 595) for white and with BS 381C (see Table 4) for other color agreed upon in accordance with ASTM Standard D1729 for compliance. If doubt exists as to the color match, an instrumental referee method may be used (ASTM Standard D2244).

6.4 Dilution Stability

There shall be no evidence of incompatibility of any of the ingredients of the paint when one volume of the paint is slowly mixed with one volume of mineral spirits (US Federal Standard No. 141, Method 4203). However, slight pigment settling shall be permitted.

6.5 Brushing Properties

The paint as packaged, shall be easily applied when tested in accordance with US Federal Standard No. 141, Method 4321. The paint shall dry to a smooth, uniform film, free from seeds, runs, sags, or streaks. The dried film shall show no discernible brush marks.

6.6 Spraying Properties

Spray apply the paint to this panel to a dry film thickness of 23-28 microns. The paint shall be easily applied when tested in accordance with US Federal Standard No. 141, Method 4331. The paint shall show no running, sagging, or streaking. The air dried film shall show no seeding, dusting, floating, fogging, mottling, hazing, excessive orange peel, or other film defect.

6.7 Adhesion

Use the panel prepared in 6.6 by air drying for 18 hours, then baking for 2 hours at 105 ±2°C. Condition the panel for one hour under referee testing conditions (see Section 9 of US Federal Standard No. 141). Then score a line through to the metal across the width of the film using a sharp pointed knife. The film shall then be taped perpendicular to and across the score line with waterproof, pressure sensitive tape, 2 cm wide, conforming of ASTM D5486. Press the tape in firm contact with pressure. Allow approximately 10 seconds for the test area to return to room temperature. Grasp the free end of the tape and at a rapid speed strip it from the film by pulling

back from the panel at approximately 180°. The paint shall show no removal of the film or loosening beyond 2 mm on either side of the score line.

6.8 Flexibility

The panel shall be prepared from new cold rolled rust free carbon steel 250 ±25 microns thick with a Rockwell 15-T maximum hardness of 82 and a finish with surface roughness of 0.2 to 0.3 micron. Air dry in a horizontal position for 18 hours, and then bake for 168 hours at 105 ±2°C. Condition the panel for ½ hour under standard testing conditions (see Section 9 of US Federal Standard No. 141). Bend over a 6 mm mandrel. Examine the coating for cracks over the area of the bend in a strong light at seven diameters magnification. The paint shall withstand the bending without cracking or flaking.

6.9 Hiding Power (Contrast Ratio)

Determine the hiding power in accordance with ASTM Standard D 2805. Draw down a film using an applicator that will deposit a dry film of 25 microns maximum thickness. Air dry for 72 hours, measure the thickness of the dried film, then measure the reflectance. Calculate the contrast ratio. A dry film thickness of 25 microns maximum of white paint (minimum reflectance 84%) shall give a dry film contrast ratio of 0.95.

TABLE 4 – COLOR

PAINT COLOR	COLOR No. TO BS 381 C
ARCTIC BLUE	112
SEA GREEN	217
BRILLIANT GREEN	221
CANARY YELLOW	309
LIGHT STRAW	384
MIDDLE BROWN	411
SIGNAL RED	537
LIGHT ORANGE	567
LIGHT GREY	631
WHITE	595

TABLE 5 – PROPERTIES

CHARACTERISTICS	REQUIREMENTS		ASTM METHOD	US FEDERAL STD. No. 141
	Min.	Max.		
FLASH POINT, PENSKY-MARTENS, CLOSED CUP, °C	30	---	D93	---
WATER, PERCENT BY WEIGHT OF PAINT	---	0.5	D95	4081
COARSE PARTICLES AND SKINS, 0.045 STANDARD SIEVE OPENING RETAINED ON (No. 325 MESH SIEVE), PERCENT BY WEIGHT OF PIGMENT	---	0.1	D185	---
VISCOSITY* SHEAR RATE 200 rpm:				
GRAMS	125	175	D562	---
KREB UNITS	67	77.0	D562	---
FINENESS OF GRIND, MICRONS	25		D1210	---
DRYING TIME:				
SET TO TOUCH, HOURS	---	2	D1640	4061
DRY HARD, HOURS	---	8	D1640	4061

* Viscosity 48 hours or more after manufacture.

7. STORAGE LIFE AND PACKAGING

7.1 Condition in Container

Determine package condition of the paint in accordance with US Federal Standard No.141 Method 3011. The paint shall be free of grit, seeds, skins, lumps, thickening, or livering and shall show no more pigment settling or caking that can be readily re-incorporated to a smooth homogeneous state.

Reseal and then agitate the can for three minutes on a paint shaker. On re-examination of the contents, the disclosure of gel bodies, undispersed pigment, or unsatisfactory settling properties is cause for rejection.

7.2 Storage Stability, Partially Full Container

Determine skinning after 48 hours in accordance with US Federal Standard No. 141, Method 3011 except use $\frac{3}{4}$ filled, 250 ml multiple friction top can. The paint shall show no skinning. Reseal and store for seven days at 60°C and observe. The paint shall show no livering, curdling, hard caking, or gummy sediment. It shall mix readily to a smooth homogeneous state.

7.3 Storage Stability, Full Container

Determine the storage stability of the package paint in accordance with ASTM Standard D1849 using a standard quart can allowing to stand undisturbed for 24 months. The paint shall show no skinning, livering, curdling hard-dry caking, or tough gummy sediment. Evaluate pigment settling or caking, but agitate the can for five minutes on the paint shaker prior to examination. The paint shall remix readily to a smooth homogeneous state and must be useable. The consistency of the paint after storage shall be 62-82 Krebs Units (ASTM Standard D562).

7.4 Packaging

The packaging shall meet the relevant requirements of ASTM D 3951 (88).

8. INSPECTION

8.1 All materials supplied under this specification shall be subject to timely inspection by the purchaser or his authorized representative. The purchaser shall have the right to reject any material(s) supplied which is (are) found to be defective under this specification. In case of dispute, the arbitration or settlement procedure, established in the procurement documents shall be followed.

8.2 Samples of any or all ingredients used in the manufacture of this paint may be requested by the purchaser and shall be supplied upon request, along with the supplier's name and identification for the material.

8.3 Unless otherwise specified the methods of sampling and testing should be in accordance with US Federal Test Method Standard No. 141 or Applicable Methods of the American Society for Testing and Materials (ASTM).

9. LABELING

9.1 Refer to ANSI Standard Z129.1 "Precautionary Labeling of Hazardous Industrial Chemicals".

9.2 Marking of Containers

Each container shall be legibly marked with the following information:

Name: Silicone Alkyd Paint as Top coat (Finish)

Specification: [IPS-M-TP-175](#)

Color: according to BS381C No.

High gloss white according to US Federal Standard 595 No. 17886.

.....
according to

MESC No. :

No of components

Maximum temperature resistance

Type of spray

Kind and size of spray nozzle tip

Cleaning material

Flash point °C

Pot life (hours)

Drying time for overcoating

Kind of thinner

Lot Number:

Stock Number:

Date of Manufacture:

Quantity of Paint in Container:

Information and Warnings, if needed,

Manufacturer's Name and Address:

Design Guide: For guidance on the usage of this paint for various application/environment and temperature range reference shall be made to [IPS-E-TP-100](#) "Paints"

9.3 Directions for Use

The following directions for use shall be supplied with each container of paint:

Directions for Use of Silicone Alkyd Paint as Top coat (Finish)

This paint is intended for use as a finish coat over a rust inhibitive primer (or other suitable primers) and an intermediate coat on structural steel. Before applying, remove all moisture, oil, grease, dirt, and loose or nonadhering paint. Sound old coatings that are compatible with this silicon alkyd paint may remain, but damaged areas or areas of poor adhesion must be spot-cleaned and spot-primed.

Mix paint thoroughly before use. If simple stirring is inadequate, pour off most of the liquid into a clean container. Thoroughly mix the pigment with the remaining liquid, taking care to scrape all the pigment off the bottom of the can. Gradually add the poured-off liquid and mix thoroughly. Mixing may be made easier by transferring contents to a larger container or by pouring the paint to-and-from another container. Examine the bottom of the container for unmixed pigment. Screen paint before applying.

Thin paint only if necessary, using only mineral spirits. For brush application under normal conditions, no thinning should be necessary. For spray applications, add up to one liter of thinner per eight liters of unthinned paint when necessary.

Apply by brush or spray to the specified film thickness or, if none is specified, to at least 38 microns, dry or approximately 63 microns, wet. The surface to be painted shall be dry; the surface temperature shall be at least 3°C above the dew point; and the temperature of the air shall be over 4°C. Do not paint outdoors in rainy weather or if freezing temperatures are expected before the paint dries.

The thinner shall be mineral spirits conforming to ASTM-D235 up to one liter of thinner may be added per eight litres of unthinned paint.

Allow paint at least 24 hours drying time in good weather before recoating.

9.4 Directions for Safety

The following directions for safety shall be supplied with each container of paint:

- Paints are hazardous because of their flammability and potential toxicity. Proper safety precautions shall be observed to protect against these recognized hazards. Safe handling practices are required and should include, but not be limited to the provisions of SSPC-PA Guide 3, "A Guide to Safety in Paint Application" and to the following:

- Keep paints away from heat, sparks, and open flame during storage, mixing, and application. Provide sufficient ventilation to maintain vapor concentration at less than 25% of the lower explosive limit.

- Avoid prolonged or repeated breathing of vapors or spray mists, and prevent contact of the paint with eyes or skin.

- Clean hands thoroughly after handling paints and before eating or smoking.

- Provide sufficient ventilation to insure that vapor concentrations do not exceed the published permissible exposure limits. When necessary, supply appropriate personal protective equipment and enforce its use.

This paint may not comply with some air pollution regulations because of its hydrocarbon solvent content.

Ingredients in this paint which may pose a hazard include lead and chromate-containing pigments and hydrocarbon solvents. Applicable regulations governing safe handling practices shall apply to the use of this paint.